

阻燃纤维胶带

FLAME RETARDANT FIBER TAPE

广州固臣实业有限公司生产的 COHESION™ (凝聚力) 阻燃纤维胶带，是以防火纤维纸为基材，单面涂覆一层阻燃胶水的胶带。

The COHESION™ (凝聚力) flame retardant fiber tape produced by GuangZhou Cohesion Industrial Co Ttd, It is based on fireproof fiber paper, Adhesive tape coated with a layer of flame retardant glue on one side.

1 应用提示 Application remarks

阻燃纤维胶带应用于变压器、电机及其它电子元件的夹层绝缘。

Flame retardant fiber tape is used as interlayer insulation in transformers, Motor and other special electronic components.

2 技术要求 Performance Requirements

2.1 外观 Appearance

材料表面应均匀、无气泡、无针孔、皱折及瑕疵之类缺陷。

The material surface should be uniformity、no air bubble、no pinhole、no crepe and blemish of objection.

2.2 性能要求 Performance requirements

表 1:阻燃纤维胶带性能要求 Table1: The standard values of flame retardant fiber tape

序号 NO.	项目 Item	单位 Units	检测值 Detection Value			
1	型号 Type		SC150			
2	总厚度 Total thickness	MM	0.09		0.13	
3	厚度允差 Thickness allowed tolerance	MM	±0.01		±0.015	
4	长度 Length	M	50		50	
5	抗拉强度 Tensile strength	N/10MM	MD≥30	XD≥11	MD≥47	XD≥18
6	延伸率 Elongation	%	MD≥6	XD≥4	MD≥7	XD≥5
7	抗撕强度 Initial tear strength	N	MD≥7	XD≥5	MD≥11	XD≥7
8	剥离强度 Peel adhesive	G/25MM	>1000		>1000	
9	击穿电压 Electric breakdown voltage	V	≥500		≥750	
10	耐温性 Temperature resistance	℃	≤180℃			

3 试验方法 Test methods

按 GB/T7125、GB/T2792、GB/T7752 中有关规定进行。

It should be in accordance with the relative stipulations of. GB/T7125、GB/T2792、GB/T7752

4 使用 Handling

4.1 检验 Inspection

出厂项目按 2.1 和 2.2。

The inspection items for routine test shall include Clause 2.1 and 2.2.

4.2 包装 Packing

包装内层为塑料薄膜，外层用纸箱包装。

Each roll shall be wrapped by plastic bag and packed by paper box.

4.3 贮存 Storage

阻燃纤维胶带贮存在室温 10~33℃, 相对湿度 45%~75% 的干燥洁净和通风的室内，不得靠近火源、暖气及受日光直射。贮存期为 6 个月，若超过贮存期按技术标准检验合格仍可使用。

The storage life is 6 months , temperature10~33℃ , relative humidity 45%~75% from the date of leaving factory The product should be stored in warehouse which is dry and clean as well as keep away from fire, heat and directly sunshine. After 6 months,it should be tested and pass all specification before use.

广州固臣实业有限公司

GUANGZHOU COHESION INDUSTRIAL CO.,LTD

广州市荔湾区龙溪大道蟠龙工业区 A 区首栋 3 楼

3/F Building First,A Section Panlong Industrial Park,Longxi Road,Guangzhou

电话/Tel: 020-81511656 传真/Fax: 020-81511659 邮箱/E-mail: gz.chs@163.com

www.020oto.com